

DULUX Super Satin Enamel for New Timber Joinery & Trim

Spec Code	NZSD0307
------------------	-----------------

Description

DULUX Super Satin semi gloss enamel is a high quality, hard wearing oil based semi gloss enamel for use on walls, doors, architraves and timber trim.

Substrate

TIMBER

SUBSTRATE DESCRIPTION

NEW TIMBER

New timber items should be delivered in a clean dry condition, just prior to installation. The timber should be inspected for physical defects, such as splinters, cracks, woolly grain, machine marks, and knot holes and also for other defects such as sap and tannin stains, and resin exudation from knots. Examine surfaces for wax or preservatives. Moisture content should be close to equilibrium moisture content, usually 10-17% for satisfactory staining or coating. Timber should be stored out of the weather before painting. Timber left exposed to the weather for as little as one month prior to painting will suffer from reduced paint adhesion and durability.

AGED TIMBER

Old timber surfaces should be inspected for dry rot, mould or fungus, excessive water content, grey and weathered timber, grain cracking, resins, stains, old unsound paint, dirt and any surface contamination. These defects should be rectified prior to painting.

TANNIN RICH TIMBER

Tannins are water-soluble extractives present in some timbers such as meranti, merbau, kwila, western red cedar and tallowwood. These tannins are leached out by water or moisture and can cause staining of surrounding areas. They are seen as dark coloured stains either under or within a coating.

Tannin staining is most obvious in light coloured coatings, such as whites. Darker and wood-toned colours hide the tannin stains best. When using light colours on tannin rich timbers, an appropriate primer should be used to seal the tannins in the wood.

Substrate Preparation

PTI003 - TIMBER

TI PREPARATION OF NEW TIMBER SURFACES

ASSESS SUITABILITY

Ensure the wood is thoroughly clean and dry before commencing. If there is any doubt, measure moisture content which must be between 10-17% before staining or finishing can commence.

REMOVE SURFACE CONTAMINANTS

Examine the surface for the presence of sap, grease, oil, wax, tannin, building marks, or other contaminants. Scrape off and remove residual contaminants by solvent cleaning. Use scraper to remove dirt and mortar splashes. Any greyed wood fibres on aged timbers need to be removed by sanding and / or suitable chemical wood cleaner.

CLEAN

Clean to remove all dirt, dust and all other surface contaminants by using a suitable cleaning agent and rinse off with clean water. Treat mould with a suitable mould treatment.

REPAIR SURFACE IMPERFECTIONS

Fill nail holes, cracks and other defects with a suitable wood filler and allow to dry thoroughly.

SANDING

Sand dressed timber with fine sandpaper in direction of the grain and along the full length of the board. Round off all sharp edges to a minimum of 2 mm radius in order to achieve an even film build and uniform paint coverage.

Specification Sheet	DULUX Super Satin Enamel for New Timber Joinery & Trim		
Spec Code	NZSD0307	Page No	1 of 2
Issue No	3.0	Date Issued	16/01/2011
Quick Spec No.			

DULUX Super Satin Enamel for New Timber Joinery & Trim

Spec Code	NZSD0307
------------------	-----------------

Coating System

	Data Sheet		Dry Film Thickness (microns)	Theoretical Spreading Rate* (square metres per litre)	Recoat**
1st Coat					
DULUX Precoat Acrylic Primer Undercoat	DD0813	Min	30	13.7	2 Hours
Brush		Max	30	13.7	Indefinite
2nd Coat					
DULUX Super Satin Semi Gloss Enamel	DD0780	Min	31	16.1	16 Hours
Brush, roller, conventional and airless spray		Max	31	16.1	Indefinite
3rd Coat					
DULUX Super Satin Semi Gloss Enamel	DD0780	Min	31	16.1	16 Hours
Brush, roller, conventional and airless spray		Max	31	16.1	Indefinite

* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness.** Recoat times are quoted for 25°C and 50% Relative humidity, these may vary under different conditions.

Important Notes

Some colours may require additional top coats to achieve coverage.

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (New Zealand) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "Orica" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road NZ ACN 133 404 118

This specification should be read in conjunction with the Product Datasheets specified within this document.

Specification Sheet	DULUX Super Satin Enamel for New Timber Joinery & Trim		
Spec Code	NZSD0307	Page No	2 of 2
Issue No	3.0	Date Issued	16/01/2011
Quick Spec No.			